

Flowable polyester molding compositions

Abstract

5 Thermoplastic molding compositions comprising

A) from 10 to 99.99% by weight of at least one thermoplastic polyester

10 B) from 0.01 to 50% by weight of a highly branched or hyperbranched polyester of
A_xB_y type where x is at least 1.1 and y is at least 2.1

C) from 0 to 60% by weight of other additives,

where the total of the percentages by weight of components A) to C) is 100%.